

# ダンラインスーパーロープ(Danline SP Rope)

原料:ポリプロピレン 特殊モノフィラメント 高強力糸  
比重:0.91

寸 法		最低引張強度				標準質量 (kg/200m)			
直 径	周 径	NK 規格		当社規格		NK 規格	三つ打ち (普通打)	三つ打ち (硬打)	クロス
mm	inch	kN	tf	kN	tf				
6	3/4			6.26	0.64		3.60	3.70	
7	7/8			8.39	0.86		4.90	5.00	
8	1			10.8	1.10		6.40	6.60	6.40
9	1 1/8			13.5	1.38		8.10	8.30	8.10
10	1 1/4	12.7	1.30	16.6	1.69	10.0	10.0	10.3	10.0
11	1 3/8			19.8	2.02		12.2	12.6	12.2
12	1 1/2	17.7	1.80	23.3	2.38	14.0	14.4	14.8	14.4
14	1 3/4	23.5	2.40	31.3	3.19	19.0	19.6	20.2	19.6
16	2	29.4	3.00	40.3	4.11	24.0	25.5	26.3	25.5
18	2 1/4	37.3	3.80	50.5	5.15	31.0	32.3	33.3	32.3
20	2 1/2	44.1	4.50	61.7	6.29	38.0	39.9	41.1	39.9
22	2 3/4	54.9	5.60	73.8	7.53	47.0	48.3	49.7	48.3
24	3	63.7	6.50	87.2	8.89	55.0	57.5	59.2	57.5
26	3 1/4	73.5	7.50	101	10.3	64.0	67.5	69.5	67.5
28	3 1/2	83.4	8.50	117	11.9	74.0	78.2	80.5	78.2
30	3 3/4	97.1	9.90	133	13.6	85.0	89.8	92.5	89.8
32	4	108	11.0	151	15.4	97.0	102	105	102
34	4 1/4			169	17.2		115	118	115
35	4 3/8	127	13.0	179	18.3	116	122	126	122
36	4 1/2			188	19.2		129	133	129
38	4 3/4			209	21.3		144	148	144
40	5	164	16.7	229	23.4	152	160	165	160
42	5 1/4			252	25.7		174	179	174
45	5 5/8	203	20.7	288	29.4	191	200	206	200
48	6			325	33.2		228	235	228
50	6 1/4	250	25.5	352	35.9	236	247	254	247
55	6 7/8	294	30.0	422	43.0	286	299	308	299
60	7 1/2	348	35.5	497	50.7	340	356	367	356
65	8	402	41.0	579	59.0	399	417	430	417
70	8 11/16	461	47.0	667	68.0	463	484	499	484
75	9 1/4	525	53.5	760	77.5	531	556	573	556
80	9 7/8	593	60.5	859	87.6	605	632	651	632
85	10 1/2	667	68.0	964	98.3	683	714	735	714
90	11 1/8	735	75.0	1070	109	765	800	824	800
95	11 3/4	814	83.0	1190	121	853	892	919	892
100	12 3/8	897	91.5	1310	134	945	988	1020	988
110	13 5/8			1580	161		1200	1240	1200
120	14 7/8			1850	189		1420	1460	1420

- (注) 1. 引張強度及び伸度は乾、湿共変化ありません。  
2. 切断時の伸度は25~30%です。  
3. 引張強度は35℃の状態における測定値です。