

ニューサンライトロープ(New Sunlight Rope)

原料:ポリプロピレン 特殊モノフィラメント
比重:0.91

寸 法		最低引張強度				標準質量 (kg / 200m)			
直 径 mm	周 径 inch	NK 規格		当社規格		NK 規格	三つ打ち (普通打)	三つ打ち (硬打)	クロス
		kN	tf	kN	tf				
6	3/4			6.12	0.62		3.60	3.70	
7	7/8			8.14	0.83		4.90	5.00	
8	1			10.4	1.06		6.40	6.60	6.20
9	1 1/8			13.0	1.32		8.10	8.30	7.80
10	1 1/4	12.7	1.30	15.7	1.61	10.0	10.0	10.3	9.70
11	1 3/8			18.8	1.92		12.2	12.6	11.8
12	1 1/2	17.7	1.80	22.1	2.25	14.0	14.4	14.8	13.9
14	1 3/4	23.5	2.40	29.3	2.99	19.0	19.6	20.2	19.0
16	2	29.4	3.00	37.6	3.83	24.0	25.5	26.3	24.2
18	2 1/4	37.3	3.80	46.7	4.76	31.0	32.3	33.3	31.1
20	2 1/2	44.1	4.50	56.8	5.79	38.0	39.9	41.1	38.0
22	2 3/4	54.9	5.60	67.7	6.90	47.0	48.3	49.7	46.9
24	3	63.7	6.50	79.5	8.11	55.0	57.5	59.2	55.2
26	3 1/4	73.5	7.50	92.2	9.40	64.0	67.5	69.5	63.8
28	3 1/2	83.4	8.50	106	10.8	74.0	78.2	80.5	73.6
30	3 3/4	97.1	9.90	120	12.3	85.0	89.8	92.5	85.2
32	4	108	11.0	135	13.8	97.0	102	105	96.7
34	4 1/4			151	15.4		115	118	110
35	4 3/8	127	13.0	160	16.3	116	122	126	116
36	4 1/2			168	17.2		129	133	122
38	4 3/4			186	19.0		144	148	135
40	5	164	16.7	205	20.9	152	160	165	152
42	5 1/4			224	22.8		174	179	167
45	5 5/8	203	20.7	254	25.9	191	200	206	191
48	6			287	29.2		228	235	218
50	6 1/4	250	25.5	309	31.5	236	247	254	236
55	6 7/8	294	30.0	369	37.6	286	299	308	286
60	7 1/2	348	35.5	433	44.2	340	356	367	340
65	8	402	41.0	502	51.2	399	417	430	399
70	8 11/16	461	47.0	576	58.8	463	484	499	463
75	9 1/4	525	53.5	655	66.8	531	556	573	531
80	9 7/8	593	60.5	738	75.2	605	632	651	605
85	10 1/2	667	68.0	825	84.1	683	714	735	683
90	11 1/8	735	75.0	917	93.5	765	800	824	765
95	11 3/4	814	83.0	1010	103	853	892	919	853
100	12 3/8	897	91.5	1120	114	945	988	1020	945
110	13 5/8			1330	136		1200	1240	1140
120	14 7/8			1560	159		1420	1460	1360

- (注) 1. 引張強度及び伸度は乾、湿共変化ありません。
2. 切断時の伸度は25~30%です。
3. 引張強度は35℃の状態における測定値です。